

Product
Data
Sheets

Architectural Specialty Solutions

Interiors + Exteriors

Formglas[®]

PRODUCT DATA SHEET

EXTERIOR FINISH CARPENTRY

Molded Architectural Products and Elements

MasterFormat® 06 20 13

GFRC-L by **Formglas®**

For Exteriors

Trade Name

Formglas® GFRC-L



Common Name(s)

Glass Fiber Reinforced Concrete | GFRC
Glassfiber Reinforced Concrete | GFRC

Manufacturer

Formglas Products Ltd.
181 Regina Road
Vaughan, Ontario, Canada L4L 8M3
T: 1.866.635.8030 F: 416.635.6588
Web: formglas.com Email: info@formglas.com



BRANDED ENTRY PEDIMENT

BROOKS BROTHERS, USA

Summary

Formglas® GFRC-L is a Class A (or 1) flame-spread rated composite material made from Portland cement, sand, aggregate and glass fiber that has good flexural strength properties. Parts are factory-molded in a hand lay-up process to make architectural elements in a variety of shapes, patterns, textures and choices of color, or, are available unfinished for on-site painting. After de-molding, unless specified as paint-ready, the exposed face of the parts is finely sandblasted to impart a uniform surface finish. Formglas® GFRC-L parts have a nominal shell thickness of 5/8" ⇔ 19 mm with perimeter edges increased to a minimum thickness of 1" ⇔ 25 mm to provide added strength. Formglas® GFRC-L does not incorporate a factory attached steel panel frame for support commonly used with larger GFRC panels. Formglas® GFRC-L is used for applications where smaller panel and part sizes can be utilized and generally offers appreciable cost advantages compared to conventional GFRC, or natural stone.

Detailed Description

Glass Fiber Reinforced Concrete (GFRC) is a designation used to refer to a broad category of cementitious products manufactured using Portland cement, silica sand, aggregate, alkali-resistant glass fiber and admixtures in different proportions to meet different performance and aesthetic requirements. In architectural applications, GFRC is most commonly associated with the large decorative panels used on building facades and cladding. These large heavy panels require a structural steel panel frame to be bonded to the inside of the molded GFRC composite material for support, which is also used to attach the GFRC panel to the building structure. Cranes are typically used in the installation of these GFRC parts.

Formglas® GFRC-L, however, is used in applications where the attributes of a molded GFRC product are desired for use on smaller panels and parts that do NOT require a steel panel

frame support system. In these applications, Formglas® GFRC-L is lighter, quicker and easier to install and more cost effective than conventional GFRC. Typically, the maximum panel size is 3' x 4' ⇔ 900 mm x 1200 mm weighing approximately 7 lbs/ft² ⇔ 34 kg/m². The cross sectional profile of a part can add strength in and of itself. This can marginally increase the overall part dimensions that can be made. Overall part weight (maximum 100 lbs) is used as a limiting factor to maintain ease of handling and installation. Formglas® GFRC-L uses white Portland cement and color pigments to provide uniform color consistency throughout the material thickness – not just the face mix. As a result of the natural properties of concrete and aggregates, and the touch-up and fine finishing process post production, minor variation in color and texture within and between parts should be expected.

Some typical architectural applications of Formglas® GFRC-L include low-rise exterior facade veneer panels and decorative elements such as cornices; pediments, window and door frames; columns; friezes; and interior elements where a hard non-combustible impact resistant material is desired. Most molded parts are secured to the building's structural framing and substrate with concealed fasteners. Parts can be supplied with factory-molded corners to minimize field cutting. Most items are custom-made to project design requirements and specifications.

Formglas® uses 5-axis CNC technology to machine precision patterns from which molds are produced to make the required parts. In situations involving complex design elements or projects, Formglas® will work with architects and designers to develop a practical plan for the parts and assemblies they envision through 3D modeling and/or scaled or full-size mock-ups. Detailed shop drawings and material samples are prepared for approval prior to manufacture.

Technical Data

Refer to the following standards:

ASTM International (ASTM)

- E84 - Standard Test Method for Surface Burning Characteristics of Building Materials
- C947 - Standard Test Method for Flexural Properties of Thin-Section Glass Fiber Reinforced Concrete
- C944 - Standard Test Method for Abrasion Resistance of Concrete or Mortar Surfaces
- C140 - Standard Test Methods for Sampling and Testing Concrete Masonry Units and Related Units
- C518 - Standard Test Method for Steady-State Thermal Transmission by Means of the Heat Flow Meter Apparatus

Physical and Mechanical Properties

Formglas® GFRC-L is a single skin GFRC composite panel made with white Portland cement, silica sand, polymer and alkali-resistant glass fiber with a high Zirconia content (minimum 16%). The composite consists of a 1/8" ± 3 mm face mix without glass fiber, and 1/2" backing mix with the glass fiber interspersed.

Matrix:	Portland cement, sand, and polymer
Finish:	Six standard colors Custom color matching available
Surface:	Lightly sandblasted or smooth if paint-ready
Density:	134 lbs/ft. ³ ± 2145 kg/m ³
Weight:	7-9 lbs/ft. ² ± 34-44 kg/m ² *
Shell thickness:	5/8" ± 16 mm nominal**
Edge thickness:	5/8" ± 16 mm minimum
Glass Fiber:	4% minimum
Max. length moldings:	4' ± 1.2 m
Max. size veneer panels:	48" x 36" ± 1200 x 900 mm
Max. size molded parts:	15 ft ² ± 1.4 m ²

* Typical weights – parts with deep surface relief, etc. may weigh more. Please submit drawings for a more accurate estimate.

** Subject to manufacturing tolerances. Weight and measurement conversions may be rounded.

ASTM Standard and ISO Test Results

Flame Spread:	0
Smoke Development:	0
Flexural Strength:	1860 psi ± 12.8 MPa
Tensile Strength:	1260 psi ± 8.7 MPa
Compressive Strength:	4000 psi ± 27.6 MPa
Coefficient of Linear Thermal Expansion:	7.6 x 10 ⁻⁶ in/in/°F ± 13.6 x 10 ⁻⁶ mm/mm/°C
Hardness (Abrasion):	0.37%
Thermal Conductivity	4.3 Btu in/h ft ² °F ± 0.62 W/m K

Manufacturing Tolerances

Dimensional (all directions):	± 3/16" ± 5 mm
Thickness:	± 1/8" ± 3 mm
Variation from square:	± 1/8" ± 3 mm
Bowing, out of plane	1/8"/ft ± 3 mm / 300 mm

LEED®



Formglas® products contribute toward LEED® credits, and have been used in LEED® projects worldwide. Since Formglas® products are usually custom-made to project specifications, their contribution to credits may vary. Contact Formglas® with specific details of your project and to clarify the version of LEED® rating system applicable.

Delivery, Storage and Handling

Formglas® GFRC-L parts shall be transported and handled in a manner that avoids damage or excessive stress. Packaging or components showing signs of damage should be marked as such on freight documents, inspected immediately, and claimed for any damage due to shipping with the freight carrier. Advise the carrier and Formglas® immediately of any damage. Formglas® GFRC-L parts shall be protected from rain, snow, sunlight, excessive weather conditions, high levels of humidity, and job site damage. Place non-staining resilient spacers between panels and support panels during storage and handling. Protect panels from dirt and damage during handling, transport and storage. Store panels on firm, level and smooth surfaces with part identification labels clearly visible, and ideally protected from harsh conditions around the job site.

Preparatory Work

Site Conditions:

Site conditions must be reviewed for compliance with Formglas' requirements, installation tolerances and any other conditions that may affect the installation and performance of Formglas® GFRC-L parts. Any unsatisfactory conditions are to be corrected prior to installation. Field measurements are to be taken to verify the dimensions, including those not shown on the drawings, and provide specific details of any changes for inclusion into the Formglas® shop drawings prior to it commencing the manufacture of custom molds and Formglas® GFRC-L parts. Formglas® will produce parts in accordance with the approved shop drawings only, and is NOT responsible for any deviations between the site conditions and the approved drawings.

Substrates:

In the case of flat veneer surface cladding solutions only, the substrates to accept Formglas® GFRC-L parts shall be surfaced with suitable materials (e.g. exterior-grade plywood) and weather barrier as applicable and installed straight and true within 1/8" in 8 linear ft. ⇔ 3 mm in 2500 mm. This is not required for columns, cornices, trims or other such applications. The substrate shall be free of obstruction and interference that prevents the correct positioning and attachment of the Formglas® GFRC-L parts. Structural framing and substrate materials shall be of the proper size and design for the intended use and shall be sufficient to properly support the installed Formglas® GFRC-L parts.

■ **Installer Safety**

Installers are to wear appropriate personal protection equipment when handling or installing Formglas® materials. This should include eye protection, gloves and dust masks. Please adhere to local regulations and rules established at the job site. Before handling and installing Formglas® materials, installers are responsible for reviewing SDS information which is readily available at www.formglas.com, or included with the crate(s) used to ship Formglas® materials, or by calling Formglas® at 1.866.635.8030.

■ **Installation**

General:

Install Formglas® GFRC-L parts as indicated on the approved shop drawings, instructions and the contract documents. The installing contractor is to supply and install all brackets and shims as required for the installation and proper alignment of the Formglas® GFRC-L parts with adjacent parts and materials. Part thicknesses may vary. Allow for shim spaces between the Formglas® GFRC-L and the substrate. Formglas® GFRC-L parts are to be attached to the framing members or substrate using corrosion resistant screws, bolts or other fasteners as shown on the shop drawings. Additional bracing, fastening points etc. not shown on the drawings, may be required to ensure a proper installation.

Cutting:

When cutting parts is required, use the most suitable cutting method listed below. Always wear goggles and a dust mask.

- A miter or table saw with diamond blade for masonry use – dry cut only.
- For small cuts or cut-outs, use a mini-grinder with 4" ⇔ 100 mm diamond blade

Attachment:

Formglas® GFRC-L parts are to be installed with concealed-fastening methods. Face-fastening will always be visible. Typically, metal mounting plates are factory-attached to the backs of panels which extend marginally beyond the part edges into joint spaces where the screws will subsequently be concealed with caulked joints. In some instances where fastening is along a top edge of a panel, flashing materials (installed by others afterward) can conceal face fasteners. Use joint spacers to maintain uniform joint spacing as indicated on the drawings. When directed, use a Formglas® recommended adhesive to prevent bleed-through (PL® Premium® marketed under Loctite® and LePage® brands.)

Joint Treatments:

- Joints must be caulked
- Formglas® does not supply caulk for joints but can recommend a brand and color of caulk for use with specific Formglas® GFRC-L colors.
- Use spacers (min. 3/8" ⇔ 9.5 mm) to maintain a uniform gap and apply masking tape on each side of the joint.
- Avoid smearing caulk beyond the joint and remove any excess immediately with a damp cloth or flexible scraper.
- Caulk between Formglas® GFRC-L and different materials.
- Do NOT attempt a monolithic look - joints cannot be hidden.

Hole Filling and Patching:

- Patch screw holes and chips carefully with matching Formglas® GFRC-L patching compound, and avoid smearing it beyond the hole. Remove excess patching compound immediately with a flexible plastic scraper and a damp cloth. Follow detailed instructions supplied with the patching compound.

**Always use patching compound sparingly
Avoid smearing it beyond the holes
Always remove excess compound immediately**

**For more details, refer to the installation
instructions and project drawings.**

■ **Cleaning and Maintenance**

- Periodic cleaning is recommended to avoid any build up of dirt and/or acidic pollutants which may affect the appearance of GFRC-L parts. Clean soiled surfaces with water and a mild household dish detergent. Surfaces may require light scrubbing with a soft-bristled brush. To avoid surface damage including etching, use of a pressure washer is not recommended.
- Always take precautions to prevent staining of adjacent materials when cleaning.

■ Applications

To view photos of Formglas® GFRC-L applications, or to contact a local Formglas® representative, visit www.formglas.com.



PERIMETER BASE

RBC BANK BRANCH, MISSISSAUGA



PATTERNED WALL PANELS

BURBERRY, LOS ANGELES



DECORATIVE WISHBONE COLUMNS & BASE PANELS

JOEY RESTAURANT, TORONTO



DECORATIVE WALL PANELS & TRIM ELEMENTS

BROOKS BROTHERS, TORONTO

PRODUCT DATA SHEET

EXTERIOR FINISH CARPENTRY

Molded Architectural Products and Elements

MasterFormat® 06 20 13

GFRC-L by **Formglas®**

For Exteriors

■ Samples Available

Formglas® GFRC-L can be fabricated to match a selection of colors and textures, or can be supplied ready for field painting. In addition, Formglas® maintains an inventory of six standard samples to demonstrate this material. To request a sample, contact samples@formglas.com or your local Formglas® representative to discuss your specific project requirements.

Please note that images and their color(s) are for general reference and may not be accurately rendered on screen or in print.



Formglas® GFRC-L

Color: Buff
Surface: Sandblasted
Sample Size: 4" x 5"
Sample Code: 98027




Formglas® GFRC-L

Color: Tan
Surface: Sandblasted
Sample Size: 4" x 5"
Sample Code: 98028



Formglas® GFRC-L

Color: Desert Sand
Surface: Sandblasted
Sample Size: 4" x 5"
Sample Code: 98029




Formglas® GFRC-L

Color: Mountain Grey
Surface: Sandblasted
Sample Size: 4" x 5"
Sample Code: 98143



Formglas® GFRC-L

Color: White Sandstone
Surface: Sandblasted
Sample Size: 4" x 5"
Sample Code: 98026



Formglas® GFRC-L

Color: Paint-Ready
Surface: Smooth
Sample Size: 4" x 5"
Sample Code: 98124

Project: Brooks Brothers, Across North America | Design: Permasteelisa Group | Material: Formglas® GFRC-L



Formglas® GFRC-L



Project: Kohl's Department Stores, Across USA | Design: Schroeder & Holt Architects, Ltd. | Material: Formglas® GFRC-L

Shaping Possibilities™

formglas.com

North America Toll Free
+1.866.635.8030

International
+1.416.635.8030

Formglas®